CLAIMS

- In a soda-lime-silica series glass, an ultraviolet and infrared absorptive greenish glass, which is characterized in that, in an expression of weight %, it comprises at least coloring components of 0.3-0.5% of total Fe₂O₃, 0.8-2.0% CeO₂, 0.8-2.0% TiO₂, and 0.10-0.25% FeO, and that the glass at 5mm thickness is 9% or less in ultraviolet transmittance (T_{uv}) according to ISO/DIS9050, 1% or less in 350nm wavelength transmittance (T_{350}), 70% or greater in 550nm wavelength transmittance (T_{550}), and 25% or less in 1100nm wavelength transmittance (T_{1100}).
- An ultraviolet and infrared absorptive greenish glass according to claim 1, which is characterized in that, in an expression of weight %, it comprises 67-75% SiO₂, 0.5-3.0% Al₂O₃, 7.0-11.0% CaO, 2.0-4.2% MgO, 12-16% Na₂O, 0.5-3.0% K₂O, and 0.05-0.3% SO₃ in addition to the coloring components of the glass, that the sum of these components and the coloring components is 98% or greater, and that SiO₂+Al₂O₃+TiO₂ amounts to 70-76%, CaO+MgO amounts to 10-15%, and Na₂O+K₂O amounts to 13-17%.
- 3. An ultraviolet and infrared absorptive greenish glass according to claim 1 or claim 2, which is characterized in that FeO/Fe₂O₃ is 0.3-0.6 in weight ratio expression and that CeO₂/TiO₂ is 0.7-1.3 in weight ratio expression.
- 4. An ultraviolet and infrared absorptive greenish glass according to any of claims 1 to 3, which is characterized in that at 5mm thickness visible light transmittance (T_v) by A light source is 67% or greater, solar radiation transmittance (T_s) is 48% or less, dominant wavelength (D) by D₆₅ light source is 510-560nm, and excitation purity (Pe) is 10% or less.

30

5

10

- 5. An ultraviolet and infrared absorptive greenish glass according to any of claims 1 to 4, which is characterized in comprising 5-50 ppm Cr₂O₃, 0-200 ppm MnO and 0-1.0% SnO as coloring components in weight % expression.
- 6. An ultraviolet and infrared absorptive greenish glass according to claim 1, which is characterized in that CeO₂ amounts to 0.8-1.5% and TiO₂ amounts to 0.8-1.5%, and that it comprises at least 0.1-0.7% SnO as a coloring component in weight % expression.
- 7. An ultraviolet and infrared absorptive greenish glass according to claim 6, which is characterized in that it comprises in weight % expression 67-75% SiO₂, 0.5-3.0% Al₂O₃, 7.0-11.0% CaO, 2.0-4.2% MgO, 12-16% Na₂O, 0.5-3.0% K₂O, and 0.05-0.3% SO₃ in addition to the coloring components of the glass, that the sum of these components and the coloring components is 98% or greater, and that SiO₂+Al₂O₃+TiO₂ amounts to 70-76%, CaO+MgO amounts to 10-15%, and Na₂O+K₂O amounts to 13-17%.
 - 8. An ultraviolet and infrared absorptive greenish glass according to claim 6 or claim 7, which is characterized in that FeO/Fe₂O₃ is 0.3-0.6 in weight ratio expression and that CeO₂/TiO₂ is 0.7-1.3 in weight ratio expression.

20

25

30

- 9. An ultraviolet and infrared absorptive greenish glass according to any of claims 6 to 8, which is characterized in that at 5mm thickness visible light transmittance (T_v) by A light source is 67% or greater, solar radiation transmittance (T_s) is 48% or less, dominant wavelength (D) by D_{65} light source is 510-560nm, and excitation purity (Pe) is 10% or less.
- 10. An ultraviolet and infrared absorptive greenish glass according to any of claims 6 to 9, which is characterized in comprising 5-30 ppm Cr₂O₃ and 0-200 ppm MnO as coloring components in weight expression.